


JUNTEADOR FLEXIBLE

VISANJUNTEX



Characteristics

This high-performance product is made with silica aggregate to prevent efflorescence, achieving excellent adhesion with a high degree of flexibility for joint sealing from 2 to 20 mm on various materials (double-fired/single-fired ceramic, terrazzo, porcelain, clinker, terracotta, marble, granite, and natural stones) in high-traffic, commercial, and residential environments, including facades, pools, and other areas in constant contact with water. All our joints feature a water-repellent effect and do not undergo volume changes after application.

Applications

Jointing for floors and wall coverings in residential settings, pools, and high-traffic areas (bars, airports, shopping centers, restaurants, etc.).

Storage

The product should be kept in its original packaging and stored in a dry place, allowing it to be preserved for up to two years.

Presentation

Heat-sealed 5 kg bags. Box of 6 bags (30 kg). Pallet of 40 boxes.

Instructions for use

- Knead by hand or machine at low speed until achieving a smooth, consistent, and lump-free texture.
 - Avoid applying in extreme temperatures, below 5 °C or above 35 °C.
 - Let it rest for 5 minutes, stir, and then apply.
 - Preferably apply with a rubber trowel or spatula.
 - Fill the joint, leaving a compact and uniform surface.
 - Once the initial gloss disappears, remove any excess product, ideally with a damp sponge.
 - Perform a final cleaning when the joint has hardened.
 - Ensure the surface is clean, free from laitance and release agents.
 - Do not apply on wet surfaces or those with loose parts.
 - Avoid application in extreme weather conditions.
 - Wait time for finishing: 20 - 30 minutes.
 - Ready for service after 24 hours (48 hours for tanks and pools).
 - Walkability: approximately 3 hours.
- Jointing after installation:
- On walls bonded with standard adhesive: 4 - 8 hours.
 - On walls bonded with quick-set adhesive: 1 - 2 hours.
 - On walls with mortar: 2 - 3 days.
 - On floors bonded with standard adhesive: 24 hours.
 - On floors bonded with quick-set adhesive: 3 - 4 hours.
 - On floors with mortar: 7 - 10 hours.

PHYSICAL AND CHEMICAL PROPERTIES

Classification according to UNE EN 13888	CG 2 W A
Appearance	White or colored powder
Mixing Water	30 ± 1 %
Bulk Density in Powder Form	1,4 g/cm ³
Bulk Density in Paste Form	1,8 g/cm ³
Abrasion Resistance (UNE-EN 12808-2)	≤ 1000 mm ³
Compression Strength (UNE-EN 12808-3)	≥ 20 N/mm ²
Flexural Strength (UNE-EN 12808-3)	≥ 4 N/mm ²
Shrinkage Determination (UNE-EN 12808-4)	≤ 2 mm/m
Water absorption at 30 min (UNE-EN 12828-5)	≤ 1 g
Water absorption at 240 min (UNE-EN 12808-5)	≤ 2 g
Yield*	0,3 - 0,4 Kg/m ²
Working Time of Paste**	60 min

* Test conducted on a 1 mm thickness, depending on the joint width.

** Test conducted under normal environmental conditions of 23°C and 55% relative humidity. Test conducted on a surface with a thickness of 5 mm.

Tile Format	Yield				
	2 mm	5 mm	10 mm	15 mm	20 mm
15 x 15	0.28	0.70	1.40	2.10	2.80
15 x 20	0.23	0.57	1.15	1.72	2.30
20 x 20	0.21	0.52	1.05	1.57	2.10
25 x 25	0.17	0.42	0.85	1.27	1.70
30 x 60	0.10	0.25	0.50	0.75	1.00
60 x 60	0.06	0.15	0.30	0.45	0.60
60 x 90	0.04	0.10	0.20	0.30	0.40



JUNTEADOR PLUS

VISANJUNTEX



Characteristics

Suitable for sealing joints from 2 to 10 mm on all types of materials (double-fired/single-fired ceramic, porcelain, terrazzo, terracotta, marble, and natural stones) in covered indoor and outdoor areas (not exposed to sun, rain, or frost) in commercial and residential environments.

Available in all colors from our color chart.

All our joints feature a water-repellent effect and do not undergo volume changes after application.

Applications

Jointing for floors and wall coverings in commercial and residential environments (hotels, private residences, etc.).

Storage

The product should be stored in its original packaging and kept in a dry place, allowing it to be stored for at least two years.

Presentation

Heat-sealed 5 kg bags. Box of 6 bags (30 kg). Pallet of 40 boxes.

Instructions for use

- Knead by hand or with a machine at low speed until a smooth, consistent, and lump-free texture is obtained.
 - Do not apply in extreme temperatures, below 5°C or above 30°C.
 - Let it rest for 5 minutes, then stir and apply.
 - Preferably apply with a rubber trowel or spatula.
 - Fill the joint, leaving the surface as compact and uniform as possible.
 - Once the initial sheen disappears, remove excess product with a damp sponge, if possible.
 - Perform final cleaning once the joint has hardened.
 - Ensure the substrate is clean and free of laitance and release agents.
 - Do not apply to wet surfaces or those with loose parts.
 - Avoid applying in extreme weather conditions.
 - Wait time before finishing: 20 - 30 minutes.
 - Ready for use after 24 hours (48 hours for tanks and pools).
 - Walkability: approximately 3 hours.
- Jointing after installation:
- On walls bonded with standard adhesive: 4 - 8 hours.
 - On walls bonded with quick-setting adhesive: 1 - 2 hours.
 - On walls with mortar: 2 - 3 days.
 - On floors bonded with standard adhesive: 24 hours.
 - On floors bonded with quick-setting adhesive: 3 - 4 hours.
 - On floors with mortar: 7 - 10 hours.

PHYSICAL AND CHEMICAL PROPERTIES

Classification according to UNE EN 13888	CG 2 W
Appearance	White or colored powder
Mixing Water	30 ± 1 %
Bulk Density in Powder Form	1,2 g/cm ³
Bulk Density in Paste Form	1,6 g/cm ³
Abrasion Resistance (UNE-EN 12808-2)	≤ 2000 mm ³
Compression Strength (UNE-EN 12808-3)	≥ 15 N/mm ²
Flexural Strength (UNE-EN 12808-3)	≥ 3,5 N/mm ²
Shrinkage Determination (UNE-EN 12808-4)	≤ 2 mm/m
Water Absorption at 30 min (UNE-EN 12828-5)	≤ 2 g
Water Absorption at 240 min (UNE-EN 12808-5)	≤ 5 g
Yield*	0,3 - 0,4 Kg/m ²
Working Time of Paste**	Approx. 60 min

* Test conducted on a 1 mm thickness, depending on the joint width.

** Test conducted under normal environmental conditions of 23°C and 55% relative humidity.

Test conducted on a surface with a thickness of 5 mm.

Tile Format	Yield				
	2 mm	3 mm	5 mm	7 mm	10 mm
15 x 15	0.25	0.37	0.62	0.87	1.25
15 x 20	0.23	0.34	0.57	0.80	1.15
20 x 20	0.19	0.28	0.47	0.66	0.95
25 x 25	0.15	0.22	0.37	0.52	0.75
30 x 30	0.10	0.15	0.25	0.35	0.50
60 x 60	0.06	0.09	0.15	0.21	0.30
60 x 90	0.05	0.07	0.12	0.17	0.25



JUNTEADOR EXTRAFINO

VISANJUNTEX



Characteristics

Made with extremely fine aggregates to achieve strong adhesion in sealing joints from 0 to 2 mm, when materials are installed edge-to-edge or flush, using all types of rectified materials (porcelain, clinker, marble, and granite). Suitable for high-traffic, commercial, and residential environments in both indoor and covered outdoor areas (not exposed to sun, rain, or frost). Available in white, beige, gray, and black. All our joints feature a water-repellent effect and do not undergo volume changes after application.

Applications

Jointing for floors and wall coverings in commercial and residential environments (hotels, private residences, etc.).

Storage

The product should be kept in its original packaging and stored in a dry place, allowing it to be stored for at least two years.

Presentation

Heat-sealed 5 kg bags. Box of 6 bags (30 kg). Pallet of 40 boxes.

Instructions for use

- Knead by hand or machine at low speed until achieving a smooth, consistent, and lump-free texture.
 - Avoid applying in extreme temperatures, below 5°C or above 30°C.
 - Let the mixture rest for 5 minutes, stir, and then apply.
 - Preferably apply with a rubber trowel or spatula.
 - Fill the joint, leaving a compact and uniform surface.
 - Once the initial gloss disappears, remove any excess product, ideally with a damp sponge.
 - Perform a final cleaning when the joint has hardened.
 - Ensure the surface is clean and free of laitance and release agents.
 - Do not apply on wet surfaces or those with loose parts.
 - Avoid application in extreme weather conditions.
 - Wait time before finishing: 20 - 30 minutes.
 - Ready for service after 24 hours (48 hours for tanks and pools).
 - Walkability: approximately 3 hours.
- Jointing after installation:
- For walls bonded with standard adhesive: 4 - 8 hours.
 - For walls bonded with quick-setting adhesive: 1 - 2 hours.
 - For walls with mortar: 2 - 3 days.
 - For floors bonded with standard adhesive: 24 hours.
 - For floors bonded with quick-setting adhesive: 3 - 4 hours.
 - For floors with mortar: 7 - 10 hours.


PHYSICAL AND CHEMICAL PROPERTIES

Classification according to UNE EN 12888	CG 2 WA
Appearance	White or colored powder
Mixing Water	35 ± 1 %
Bulk Density in Powder Form	1,1 g/cm ³
Bulk Density in Paste Form	1,4 g/cm ³
Abrasion Resistance (UNE-EN 12808-2)	≤ 2000 mm ³
Compression Strength (UNE-EN 12808-3)	≥ 15 N/mm ²
Flexural Strength (UNE-EN 12808-3)	≥ 3,5 N/mm ²
Shrinkage Determination (UNE-EN 12808-4)	≤ 2 mm/m
Water Absorption at 30 min (UNE-EN 12828-5)	≤ 2 g
Water Absorption at 240 min (UNE-EN 12808-5)	≤ 5 g
Yield*	0,3 - 0,4 Kg/m ²
Working Time of Paste**	Approx. 60 min

* Test conducted on a 1 mm thickness, depending on the joint width.

** Test conducted under normal environmental conditions of 23°C and 55% relative humidity. Test conducted on a surface with a thickness of 5 mm.

Tile Format	Yield	
	1 mm	2 mm
15 x 15	0.052	0.140
15 x 20	0.046	0.092
20 x 20	0.042	0.084
25 x 25	0.033	0.066
30 x 60	0.021	0.042
60 x 60	0.012	0.024
60 x 90	0.008	0.016



JUNTEADOR PISCINAS - FUNGICIDA

VISANJUNTEX



Characteristics

Specially designed for joints from 2 to 10 mm in floors and wall coverings of vitrified ceramic mosaics, such as glass tiles and other lightweight mosaics, in pools, shower trays, and other areas in constant contact with water.

Available in white, with the option to manufacture in any color from our color chart.

All our joints feature a water-repellent effect and do not undergo volume changes after application.

Applications

Suitable for indoor, outdoor, and humid environments. Offers good workability and ease of cleaning.

Storage

The product should be stored in its original packaging and kept in a dry place, allowing it to be stored for at least two years.

Presentation

Heat-sealed 5 kg bags. Box of 6 bags (30 kg). Pallet of 40 boxes.

Instructions for use

- Knead by hand or with a machine at low speed until achieving a smooth, consistent, and lump-free texture.
 - Do not apply in extreme temperatures, below 5°C or above 30°C.
 - Let rest for 5 minutes, then stir and apply.
 - Preferably apply with a rubber trowel or spatula.
 - Fill the joint, ensuring the surface is as compact and uniform as possible.
 - Once the initial gloss disappears, remove any excess product, ideally with a damp sponge.
 - Perform final cleaning once the joint has hardened.
 - Ensure the substrate is clean, free of laitance and release agents.
 - Do not apply on wet surfaces or those with loose parts.
 - Avoid applying in extreme weather conditions.
 - Wait time for finishing: 20 - 30 minutes.
 - Ready for use after 24 hours (48 hours for tanks and pools).
 - Walkability: approximately 3 hours.
- Jointing after installation:
- For walls bonded with standard adhesive: 4 - 8 hours.
 - For walls bonded with quick-setting adhesive: 1 - 2 hours.
 - For walls with mortar: 2 - 3 days.
 - For floors bonded with standard adhesive: 24 hours.
 - For floors bonded with quick-setting adhesive: 3 - 4 hours.
 - For floors with mortar: 7 - 10 hours.

PHYSICAL AND CHEMICAL PROPERTIES

Classification according to UNE EN 12888	CG 2 W A
Appearance	White or colored powder
Mixing Water	30 ± 1 %
Bulk Density in Powder Form	1,2 g/cm ³
Bulk Density in Paste Form	1,6 g/cm ³
Abrasion Resistance (UNE-EN 12808-2)	≤ 900 mm ³
Compression Strength (UNE-EN 12808-3)	≥ 15 N/mm ²
Flexural Strength (UNE-EN 12808-3)	≥ 3,5 N/mm ²
Shrinkage Determination (UNE-EN 12808-4)	≤ 2 mm/m
Water absorption at 30 min (UNE-EN 12828-5)	≤ 2 g
Water absorption at 240 min (UNE-EN 12808-5)	≤ 5 g
Yield	0,3 - 0,4 (Kg/m ²)
Working Time of Paste**	Approx. 60 min

* Test conducted on a 1 mm thickness, depending on the joint width.

** Test conducted under normal environmental conditions of 23°C and 55% relative humidity. Test conducted on a surface with a thickness of 5 mm.

Tile Format	Yield		
	2 mm	3 mm	5 mm
15 x 15	0.25	0.37	0.62
15 x 20	0.21	0.31	0.52
20 x 20	0.19	0.28	0.47

