

JUNTEADOR PLUS

VISANJUNTEX



Characteristics

Suitable for sealing joints from 2 to 10 mm on all types of materials (double-fired/single-fired ceramic, porcelain, terrazzo, terracotta, marble, and natural stones) in covered indoor and outdoor areas (not exposed to sun, rain, or frost) in commercial and residential environments.

Available in all colors from our color chart.

All our joints feature a water-repellent effect and do not undergo volume changes after application.

Applications

Jointing for floors and wall coverings in commercial and residential environments (hotels, private residences, etc.).

Storage

The product should be stored in its original packaging and kept in a dry place, allowing it to be stored for at least two years.

Presentation

Heat-sealed 5 kg bags. Box of 6 bags (30 kg). Pallet of 40 boxes.

Instructions for use

- Knead by hand or with a machine at low speed until a smooth, consistent, and lump-free texture is obtained.
 - Do not apply in extreme temperatures, below 5°C or above 30°C.
 - Let it rest for 5 minutes, then stir and apply.
 - Preferably apply with a rubber trowel or spatula.
 - Fill the joint, leaving the surface as compact and uniform as possible.
 - Once the initial sheen disappears, remove excess product with a damp sponge, if possible.
 - Perform final cleaning once the joint has hardened.
 - Ensure the substrate is clean and free of laitance and release agents.
 - Do not apply to wet surfaces or those with loose parts.
 - Avoid applying in extreme weather conditions.
 - Wait time before finishing: 20 - 30 minutes.
 - Ready for use after 24 hours (48 hours for tanks and pools).
 - Walkability: approximately 3 hours.
- Jointing after installation:
- On walls bonded with standard adhesive: 4 - 8 hours.
 - On walls bonded with quick-setting adhesive: 1 - 2 hours.
 - On walls with mortar: 2 - 3 days.
 - On floors bonded with standard adhesive: 24 hours.
 - On floors bonded with quick-setting adhesive: 3 - 4 hours.
 - On floors with mortar: 7 - 10 hours.

PHYSICAL AND CHEMICAL PROPERTIES

Classification according to UNE EN 13888	CG 2 W
Appearance	White or colored powder
Mixing Water	30 ± 1 %
Bulk Density in Powder Form	1,2 g/cm ³
Bulk Density in Paste Form	1,6 g/cm ³
Abrasion Resistance (UNE-EN 12808-2)	≤ 2000 mm ³
Compression Strength (UNE-EN 12808-3)	≥ 15 N/mm ²
Flexural Strength (UNE-EN 12808-3)	≥ 3,5 N/mm ²
Shrinkage Determination (UNE-EN 12808-4)	≤ 2 mm/m
Water Absorption at 30 min (UNE-EN 12828-5)	≤ 2 g
Water Absorption at 240 min (UNE-EN 12808-5)	≤ 5 g
Yield*	0,3 - 0,4 Kg/m ²
Working Time of Paste**	Approx. 60 min

* Test conducted on a 1 mm thickness, depending on the joint width.

** Test conducted under normal environmental conditions of 23°C and 55% relative humidity.

Test conducted on a surface with a thickness of 5 mm.

Tile Format	Yield				
	2 mm	3 mm	5 mm	7 mm	10 mm
15 x 15	0.25	0.37	0.62	0.87	1.25
15 x 20	0.23	0.34	0.57	0.80	1.15
20 x 20	0.19	0.28	0.47	0.66	0.95
25 x 25	0.15	0.22	0.37	0.52	0.75
30 x 60	0.10	0.15	0.25	0.35	0.50
60 x 60	0.06	0.09	0.15	0.21	0.30
60 x 90	0.05	0.07	0.12	0.17	0.25

